AKOYA LAVENDER
PC13-005

MAYER FABRICS



CLEANING
PC: Privacy Curtains Cleaning Info - Wash Cycle: Process Cubicle fabric as any ordinary colored fabric, temperature not to exceed 160F. Use a synthetic detergent. Add softener to the last rinse cycle. Extracting Cycle: Fabric requires no more than 2-4 min. extracting, depending on size of load and equipment used. Drying Cycle: Do not overload dryer. Tumble dry for 3-5 min. on synthetic cycle 110F. As with all polyester fabrics, excessive heat will detract from the permanent press characteristics of this fabric. Finishing: If fabric is folded upon completion of the drying cycle, no finishing is required. Occasional light touch-up with a hand iron (275F max), or using a flat bed press with covered head may be desired for smoother seams. Important: Use cover cloth between fabric and iron or pressing head. Avoid prolonged contact with heat. Notes: Do not use caustic soap or bleach. Do not put through a mangler.

Additional cleaning details at www.mayerfabrics.com

CATEGORY
Privacy Curtain

PROPERTIES

CONTENT
55% Polyester/45% FR Polyester

FINISH
None

WIDTH
72"

WEIGHT
12.24

SHOWN RAILROADED
Yes

DIRECTIONALITY
Yes

ROLL LENGTH
60

VISUAL REPEAT
10.0, 27.04

BREAKING STRENGTH
Warp: 100.0 lbs. / Fill: 100.0 lbs.

SEAM SLIPPAGE
Warp: 97.0 lbs. / Fill: 66.0 lbs.

ABRASION RESISTANCE
n/a

PILLING RESISTANCE
Class: n/a

COLORFASTNESS TO CROCKING
Dry: Class 4 / Wet: Class 3

COLORFASTNESS TO LIGHT
60 hours

© Mayer Fabrics 2025

Specifications are subject to change. Current specifications are available at mayerfabrics.com
Mayer Fabrics | 500 S. Kitley Ave, Indianapolis, IN 46219

TF. 800.428.4415
T. 317.267.2626
F. 317.267.2629