


AKOYA AQUA

PC13-013

MAYER FABRICS



CATEGORY

Privacy Curtain

PROPERTIES



CONTENT

55% Polyester/45% FR Polyester

FINISH

None

WIDTH

72"

WEIGHT

12.24

SHOWN RAILROADED

Yes

DIRECTIONALITY

Yes

ROLL LENGTH

60

VISUAL REPEAT

10.0, 27.04

BREAKING STRENGTH

Warp: 100.0 lbs. / Fill: 100.0 lbs.

SEAM SLIPPAGE

Warp: 97.0 lbs. / Fill: 66.0 lbs.

ABRASION RESISTANCE

n/a

PILLING RESISTANCE

Class: n/a

COLORFASTNESS TO CROCKING

Dry: Class 4 / Wet: Class 3

COLORFASTNESS TO LIGHT

60 hours

CLEANING

PC: Privacy Curtains Cleaning Info - Wash Cycle: Process Cubicle fabric as any ordinary colored fabric, temperature not to exceed 160F. Use a synthetic detergent. Add softener to the last rinse cycle. Extracting Cycle: Fabric requires no more than 2-4 min. extracting, depending on size of load and equipment used. Drying Cycle: Do not overload dryer. Tumble dry for 3-5 min. on synthetic cycle 110F. As with all polyester fabrics, excessive heat will detract from the permanent press characteristics of this fabric. Finishing: If fabric is folded upon completion of the drying cycle, no finishing is required. Occasional light touch-up with a hand iron (275F max), or using a flat bed press with covered head may be desired for smoother seams. Important: Use cover cloth between fabric and iron or pressing head. Avoid prolonged contact with heat. Notes: Do not use caustic soap or bleach. Do not put through a mangle.

[Additional cleaning details at www.mayerfabrics.com](http://www.mayerfabrics.com)